

PCTWORLD INTELLECTUAL PRO
International

INTERNATIONAL APPLICATION PUBLISHED UNDER



(51) International Patent Classification⁶ :
A61K 7/16

A1**(11)****NO 9609033A1**

(43) International Publication Date: 28 March 1996 (28.03.96)

(21) International Application Number: PCT/EP95/03560

(22) International Filing Date: 9 September 1995 (09.09.95)

(30) Priority Data:
94306904.7 21 September 1994 (21.09.94) EP
(34) Countries for which the regional or
international application was filed: AT et al.

(71) Applicant (for all designated States except US): CROSFIELD
LIMITED (GB/GB); Bank Quay, Warrington WA5 1AB
(GB).

(72) Inventor; and

(75) Inventor/Applicant (for US only): STANIER, Peter, William
[GB/GB]; 66 Grange Way, Elworth, Sandbach, Cheshire
CW11 9ES (GB).

(74) Agent: HUGOT, Alain, E., P.; Unilever plc, Patent Division,
Colworth House, Sharnbrook, Bedford MK44 1LQ (GB).

(81) Designated States: AM, AT, AU, BB, BG, BR, BY, CA, CH,
CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IS, JP, KE,
KG, KP, KR, KZ, LK, LR, LT, LU, LV, MD, MG, MK,
MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI,
SK, TJ, TM, TT, UA, UG, US, UZ, VN, European patent
(AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC,
NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA,
GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW,
SD, SZ, UG).

Published

With international search report.

*Before the expiration of the time limit for amending the
claims and to be republished in the event of the receipt of
amendments.*

(54) Title: GRANULAR COMPOSITIONS

(57) Abstract

Granular composition comprising 45 to 98 % w/w of a water insoluble particulate, whereby 10 to 75 % of the water insoluble particulate is made from a water insoluble particulate material, having a weight mean particle size of less than 20 microns and an oil absorption capacity of 60 to 180 g/100 g and 10 to 75 % of the water insoluble particulate is made from a water insoluble particulate material, having a weight mean particle size of below 20 microns and an oil absorption 200 to 350 g/100 g, the granular composition having a particle size, by sieve analysis, of 95 % below 600 microns and 95 % above 40 microns.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo			SE	Sweden
CH	Switzerland	KR	Republic of Korea	SI	Slovenia
CI	Côte d'Ivoire	KZ	Kazakhstan	SK	Slovakia
CM	Cameroon	LI	Liechtenstein	SN	Senegal
CN	China	LK	Sri Lanka	TD	Chad
CS	Czechoslovakia	LU	Luxembourg	TG	Togo
CZ	Czech Republic	LV	Latvia	TJ	Tajikistan
DE	Germany	MC	Monaco	TT	Trinidad and Tobago
DK	Denmark	MD	Republic of Moldova	UA	Ukraine
ES	Spain	MG	Madagascar	US	United States of America
FI	Finland	ML	Mali	UZ	Uzbekistan
FR	France	MN	Mongolia	VN	Viet Nam
GA	Gabon				

GRANULAR COMPOSITIONSField of the Invention

5 The present invention relates to granular compositions which provide useful sensorially-perceived benefits in toothpaste compositions.

Background of the Invention

10

The use of water as a binder for silica particles has been disclosed in GB1,365,516 and water is known as a common binder for size enlargement (Handbook of Powder Technology - Vol 1 - Particle Size Enlargement - page 41, Table 2.3 - Elsevier).

15

20

25

30

Toothpaste formulations containing a granular composition comprising a water insoluble material and a water insoluble binder has been disclosed in EP-B-269,966. Such granular composition can contain functional substances such as medicaments, enzymes and polishing agents. The problem addressed by this document is that it is not possible to bind the particles within the granular composition with water soluble binders for use in formulations containing large amounts of water, such as toothpastes. The reason being that the water soluble binder will dissolve in the aqueous component of the formulation and weaken the granular composition making it impossible to detect the coarse particles in the mouth.

The addition of a zinc salt, as an anti-plaque agent, into a toothpaste composition has already been disclosed in GB 1,373,001.

It has been found that granule compositions containing only water insoluble particulates of low to medium structure, particularly those with low oil absorption capacity favoured as abrasives and polishing agents in dental formulations, bound together with water and dried are too weak to survive the normal processes in toothpaste manufacture and therefore would not be felt in the subsequent tooth cleaning process.

Additionally, granule compositions containing high structured water insoluble particulates (i.e. with high oil absorption capacity) for example silicas favoured as thickening agents in toothpaste formulations, are considered to have too much strength and give unacceptable levels of mouthfeel.

To overcome this problem it has been discovered that granular compositions of sufficient strength can be prepared by mixing a high structured water insoluble particulate with a low to medium structured one prior to the binding process. Surprisingly the addition of powdered therapeutic agents e.g. zinc citrate, opacifiers e.g. titanium dioxide and coloured pigments have been shown to have no significant detrimental effect on the properties of the granular composition.

Standard Procedures

The granular compositions of the invention are defined in terms of the properties and texture of the water insoluble particulates used to produce the agglomerate, its particle size distribution, and strength.

i) Oil Absorption

The oil absorption is determined by the ASTM spatula rub-out method (American Society Of Test Material Standards D, 281).

The test is based on the principle of mixing linseed oil with the water insoluble particulate by rubbing with a spatula on a smooth surface until a stiff putty-like paste is formed which will not break or separate when it is cut with a spatula. The volume of oil used is converted to weight and expressed as g of oil / 100g of water insoluble particulate.

ii) Weight Mean Particle Size

The weight mean particle size of the water insoluble particulate before agglomeration is determined using a Malvern Mastersizer model X, made by Malvern Instruments, Malvern, Worcestershire with MS15 sample presentation unit. This instrument uses the principle of mie scattering, utilising a low power He/Ne laser. The water insoluble particulates are dispersed ultrasonically in water for 5 minutes to form an aqueous suspension and then mechanically stirred before they are subjected to the measurement procedure outlined in the instruction manual for the instrument, utilising a 45 mm lens in the detector system.

The Malvern Particle Sizer measures the weight particle size of the water insoluble particulate. The weight mean particle size (d_{50}) or 50 percentile, the 10 percentile (d_{10}) and the 90 percentile (d_{90}) are easily obtained from the data generated by the instrument.

iii) Granule Composition Strength

The weight mean particle size distribution of the granular composition is measured using the same Malvern instrument and general method described above, but with the following differences:

- a) the granules are measured with a 300 mm lens in the detector system.
- b) an initial particle size distribution of the granules is taken with no ultrasonic dispersion (0 ultrasonics) i.e. sample dispersed with mechanical stirring only.
- c) the granules are dispersed using ultrasonics for two minutes, setting 50, and then subjected to the usual measurement procedure (50 ultrasonics).
- d) the granules are dispersed using ultrasonics for two minutes, setting 100, and then subjected to the usual measurement procedure (100 ultrasonics).

The d10, d50 and d90 can then be interpolated from the particle size distribution generated by the instrument and the higher the values obtained after the exposure to ultrasonics the stronger the granular composition.

iv) Particle Size Distribution by Sieve Analysis

A more accurate measure of the true particle size distribution of the granular composition is done using sieve analysis.

100g of the sample is placed on the top sieve of a series of BS sieves, at approximately 50 micron intervals between 45 and 600 microns. The sieves are arranged in order with the finest at the bottom and the

coarsest at the top of the stack. The sieves are placed in a mechanical vibrator e.g. Inclyno Mechanical Sieve Shaker by Pascall Engineering Co Ltd., covered with a lid and shaken for 10 minutes.

Each sieve fraction is accurately weighed and the results calculated:

$$\% \text{ residue} = \frac{\text{Wt. of residue} * 100}{\text{Wt. of sample}}$$

A particle size distribution can then be plotted from the data.

General Description of the Invention

It is a first object of the present invention to provide a granular composition comprising 45 to 98 % w/w of a water insoluble particulate, whereby 10 to 75% of the water insoluble particulate is made from a water insoluble particulate material, having a weight mean particle size of less than 20 microns and an oil absorption capacity of 60 to 180g/100g, and selected from the group consisting of amorphous silicas, aluminas, calcium carbonates, dicalcium phosphate, tribasic calcium phosphates, insoluble sodium metaphosphate, calcium pyrophosphates, hydroxyapatites, perlites, zeolites, magnesium carbonate, pumice and 10 to 75% of the water insoluble particulate is made from a water insoluble particulate material, having a weight mean particle size of below 20 microns and an oil absorption 200 to 350g/100g, selected from the group consisting of amorphous silicas, low density aluminas and expanded perlites, the granular composition having a particle size, by sieve analysis, of 95% below 600 microns and 95% above 40 microns.

This granular composition is substantially free of organic or inorganic binder.

5 It is preferable that the granular composition should have a particle size distribution, as measured by sieve analysis, such that 95% of the granules are less than 400 microns and 95% of the particles are above 100 microns, most preferably 150 microns.

10 Owing to the porous nature of the agglomerates, it is possible for them to act as delivery vehicles for substances that give cosmetic benefits such as colouring pigments, flavours, perfumes or other cosmetic. The agglomerates can also contain other cosmetic and/or
15 therapeutic dental and/or oral actives and release them into mouth. Such substances may be contained within the pores of the material. The inclusion of a material having a therapeutic or cosmetic effect on the gums or teeth or oral cavity into these agglomerates provides for a further
20 benefit in that upon crushing or collapsing of these agglomerates, the therapeutic/cosmetic agent is slowly released, thus delivering the therapeutic agent over to the mouth over a longer period of time. Suitable examples of such therapeutic agents are zinc salts such as zinc citrate;
25 antimicrobial agents such as Triclosan; anti-carries agents such as sodium fluoride and sodium monofluorophosphate; anti-plaque agents such as stannous pyrophosphate etc.

30 In this respect it has surprisingly been found, that the inclusion of zinc citrate in the agglomerates (in an amount of up to 15 %, preferably up to 12 % by weight of the agglomerates) significantly reduced the level of astringency, perceived by trained panellists upon testing a toothpaste with such agglomerates for their sensory
35 properties.

5 The addition of TiO_2 as an opacifying agent at a concentration of 1 to 5% w/w, usually at the expense of the water insoluble particulates, ensures that the granules have a white appearance and therefore stand out in coloured toothpaste formulations.

10 If coloured granules are required, then suitable food grade coloured pigments, for example pigment dispersions under the Cosmenyl trade name or pigment powders under the Hostaperm trade name or Cosmetic Pink RC 01 (D & C Red No 30) supplied by Hoechst, can be added to the composition of the granule, without affecting the strength of the granule.

15 If titanium dioxide and therapeutic agent are omitted from the granular composition containing abrasive and thickening silicas, then the coarse particles are invisible in transparent gel formulations.

20 Moreover, the agglomerate strength can be varied over a wide range by changing the water insoluble particulate structure, i.e. low structure water insoluble particulates decrease strength whereas high structure water insoluble particulates increase agglomerate strength.

25 The use of water insoluble particulates which already have an approved role in toothpastes formulations, such as toothpaste abrasive silicas [e.g. Sorbosil AC77 (obtainable from Crosfield Limited - England)] as the low/medium structure component, is an added advantage since such
30 silicas are capable of providing extra cleaning to the formulation and have good compatibility with the formulation. Indeed, particularly preferred water insoluble particulates which make up the granular composition are mixtures of synthetic, amorphous thickening [e.g. Sorbosil

TC15 (obtainable from Crosfield Limited - England)] and abrasive silicas.

5 The agglomerates should be insoluble in the medium of the toothpaste composition into which it is incorporated. In this context, "insoluble" means having insufficient solubility at ambient temperature in that the agglomerates remain undissolved or substantially undissolved in the composition such that their friability under the conditions
10 of use of the composition and thus their ability to perform their cleaning/polishing function are not deleteriously affected. Preferably, the level of insolubility of the agglomerates extend to their insolubility in the oral environment in which the composition is used, which may
15 frequently contain higher levels of water than for example a toothpaste, owing to the presence of saliva and added water frequently used in the brushing regime.

20 When the granules are incorporated in a toothpaste composition, it is important that they break down under the shear forces generated by the toothbrush in a relatively short period of time, whereby the gritty feel experienced by the user is eliminated.

25 This means, that the agglomerates should have a particle strength such that they will collapse within the range of shear and/or crush forces normally produced in the relevant brushing regime, since the considerably variable forces produced at a particular location over time enable at least
30 some of the agglomerates to survive intact long enough to perform their cleaning function to a satisfactory degree.

It is even possible to tailor the breakdown time of the agglomerates, such as to control the contact time for a
35 given duration of brushing of the composition, by

controlling the average crush strength of the agglomerates, for example by selecting a particular type of source of the particulate materials and/or the manner in which they agglomerate in the manufacturing process.

5

When the agglomerates break up under the action of shear and/or crush forces, the resulting average particle size (diameter) will typically be less than about 40 microns. Such reduced particle sizes will generally avoid any feeling of grittiness in the mouth, and impart a feeling of polished teeth.

10

It is another object of the present invention to provide a process for producing a granular composition wherein, 10 to 75 parts by weight of a water insoluble particulate material, having a weight mean particle size of less than 20 microns and an oil absorption capacity of 60 to 180g/100g, and selected from the group consisting of amorphous silicas, aluminas, calcium carbonates, dicalcium phosphate, tribasic calcium phosphates, insoluble sodium metaphosphate, calcium pyrophosphates, hydroxyapatites, perlites, zeolites, magnesium carbonate, pumice are mixed with 10 to 75 parts by weight of a water insoluble particulate material, having a weight mean particle size of below 20 microns and an oil absorption 200 to 350g/100g, selected from the group consisting of amorphous silicas, low density aluminas and expanded perlites, then agglomerated with water, the resulting product being then dried.

15

20

25

Preferably, the water insoluble particulate powders are high and low to medium structure amorphous silica particles and a therapeutic agent is mixed with them prior to agglomeration. If opaque granules are required, then TiO_2 is added to the powder mixture. If coloured granules are required, a

30

suitable food grade coloured pigment dispersion can be added.

5 By drying the product after agglomeration, a granular composition is obtained which is stable in a toothpaste composition.

10 Agglomeration can be achieved for example by pan granulation, extrusion, spray granulation or spinning disc granulation.

15 Preferably, the agglomeration is operated in a pan granulator, when the water:solids (i.e. water insoluble particulates with optionally TiO_2 /therapeutic agent etc. blended) ratio is in the range 1.1-1.35:1. This ratio is important to achieve agglomerates of correct strength, since below this the material remains a powder and above this a paste is formed.

20 Then the agglomerates are dried. This drying can be done in several ways, e.g. in an oven or in a fluidized bed. During this drying stage, the required degree of strength is built into the agglomerates.

25 It has also been found that agglomeration can be achieved by compacting the powder mixture and in this process a drying stage is not required.

30 It is therefore another object of the present invention to provide a process for producing a granular composition wherein, 10 to 75 parts by weight of a water insoluble particulate material, having a weight mean particle size of less than 20 microns and an oil absorption capacity of 60 to 180g/100g, and selected from the group consisting of
35 amorphous silicas, aluminas, calcium carbonates, dicalcium

phosphate, tribasic calcium phosphates, insoluble sodium metaphosphate, calcium pyrophosphates, hydroxyapatites, perlites, zeolites, magnesium carbonate, pumice are mixed with 10 to 75 parts by weight of a water insoluble particulate material, having a weight mean particle size of below 20 microns and an oil absorption 200 to 350g/100g, selected from the group consisting of amorphous silicas, low density aluminas and expanded perlites, the resulting blend being agglomerated by compaction.

For incorporation into toothpastes, it is important that virtually all particles are below 600 μm , preferably below 400 μm since gritty particles give unpleasant mouthfeel properties. A size reduction step utilizing minimum energy to prevent unnecessary breakdown of the agglomerate is therefore required.

One or more sieving steps are then desirable to ensure no oversize material and also to provide a bottom cut at e.g. 150 microns.

Specific Description of the Invention

The present invention will be further illustrated in the following examples.

Comparative Example 1

Two silicas of high structure [Sorbosil TC15 (obtainable from Crosfield Limited - England)] and medium (bordering upon low) structure [Sorbosil AC77 (obtainable from Crosfield Limited - England)] were agglomerated individually at 200g powder batch size, laboratory scale with de-ionised water (water:solids ratio of 1.33:1) using a Sirman CV6

mixer, supplied by Metcalfe Catering Equipment Ltd, Blaenau Ffestiniog, Wales.

The resulting wet agglomerates were then dried in an oven at 150°C for 4 hours, gently forced through a 420 micron screen and sieved at 150 microns to adjust the particle size distribution.

The silicas have the following properties:

PROPERTY	SORBOSIL TC15 (*)	SORBOSIL AC77 (*)
OIL ABSORPTION (g/100g)	315	120
WEIGHT MEAN d_{10}	5.6	2.7
PARTICLE SIZE d_{50}	12.9	8.1
(microns) d_{90}	29.3	17.8
SURFACE AREA (m^2g^{-1})	260	120

(*) - obtainable from Crosfield Limited - England

The granular silicas after agglomeration have the following properties:

	Ultrasonics	d10	d50	d90
Sorbosil TC15	0	268	415	549
	50	249	410	553
	100	70	265	469
Sorbosil AC77	0	16	187	346
	50	3.2	10	37.4
	100	2.9	8.5	21.2

The high structured silica TC15 (obtainable from Crosfield Limited - England) forms an agglomerate which is too strong and will not break down in the required time with brushing in a toothpaste composition, whilst the medium/low structured silica AC77 (obtainable from Crosfield Limited - England) produces an agglomerate which is too weak to survive the normal processes in toothpaste manufacture.

Example 1

The silicas used in comparative example 1 were blended together with titanium dioxide in the following matrix, which includes the individual silicas with TiO_2 :

	Comp. 1 parts by wt	Comp. 2 parts by wt	Comp. 3 parts by wt	Comp. 4 parts by wt	Comp. 5 parts by wt
SORBOSIL TC15 (*)	97.0	72.75	48.5	24.25	0
SORBOSIL AC77 (*)	0	24.25	48.5	72.75	97.0
TiO_2	3.0	3.0	3.0	3.0	3.0

(*)-obtainable from Joseph Crosfield & Sons - England

De-ionised water was added to the powder mixes to give a water:solids ratio of 1.33 to 1 and the resulting 200g blends were agglomerated using a laboratory scale Sirman CV6 mixer, supplied by Metcalfe Catering Equipment Ltd, Blaenau Ffestiniog, Wales.

The resulting wet agglomerates were then dried in an oven at 150°C for 4 hours, gently forced through a 420 micron screen and sieved at 150 microns to adjust the particle size distribution.

5

The resultant agglomerates have the following properties:

		<u>Ultrasonics</u>	<u>d10</u>	<u>d50</u>	<u>d90</u>
10	Composition 1	0	258	404	555
		50	254	389	547
		100	128	309	500
	Composition 2	0	228	370	542
15		50	201	355	530
		100	118	277	474
	Composition 3	0	207	351	534
		50	167	320	509
20		100	5.3	73	220
	Composition 4	0	176	324	506
		50	4	15.6	71
		100	3.4	11	29.8
25	Composition 5	0	8.8	186	332
		50	2.8	9.4	31.6
		100	2.6	8.3	21.1
30	Compositions 1 & 5 show that the addition of TiO ₂ has no detrimental effect on particle strength of the agglomerate. It can be seen that particle strength varies according to the relative amounts of high and medium/low structure silicas present in the agglomerate.				
35	Compositions 1 & 2 are considered to be too strong and				

compositions 4 & 5 too weak for an optimum strength granule. Composition 3, whilst not optimum is considered to be within the desired range for strength.

5 Example 2

The following powders were blended together to give an intimate mixture:

	1	2
	parts by weight	parts by weight
Sorbosil AC77 (*)	43.15	48.5
Sorbosil TC15 (*)	43.15	48.5
15 Titanium Dioxide	3.0	3.0
Zinc citrate trihydrate	10.7	0

(*)-obtainable from Crosfield Limited - England

20 Water was added to this mixture to give a water:solids ratio of 1.33 to 1, the resulting blend being granulated in a 100 litre CMG mixer/granulator made by Eurovent Ltd, Fenton, Stoke-on-Trent, with a 6 Kg batch charge.

25 The resulting wet agglomerates were then partially dried for 30 minutes in a fluid bed drier and finished in an oven for 2 hours at a temperature of 120 °C. The particle size distribution was adjusted by screening at 150 and 400 microns. The properties of the granular composition are outlined below.

	<u>Ultrasonics</u>	<u>d10</u>	<u>d50</u>	<u>d90</u>
Composition 1	0	193	334	502
	50	112	289	475
35	100	3.3	14.3	41.5

Composition 2	0	268	391	539
	50	224	365	526
	100	3.3	12	39

5 Clearly, the presence of zinc citrate has little effect
on the strength of the granular compositions and
granules of this strength have been shown to survive the
normal processing conditions used in toothpaste
10 manufacture, be stable in and have good sensory
properties in a toothpaste composition.

Examples 3-7:

The following homogeneous powder blends were made:

15

20

25

30

INGREDIENT	EX3	EX4	EX5	EX6	EX7
SORBOSIL AC77	41.0	36.0	24.5	40.3	47.85
SORBOSIL TC15	41.0	36.0	24.5	13.4	47.85
TRICLOSAN	4.3				4.3
STANNOUS PYROPHOSPHATE		14.3			
ZINC CITRATE TRIHYDRATE	10.7	10.7	6.3		
TITANIUM DIOXIDE	3.0	3.0	3.0	3.0	
POTASSIUM NITRATE			41.7		
POTASSIUM CITRATE				43.3	

De-ionised water was added to the powder mixes (200g) to give a water:solids ratio of 1.33 to 1 for examples 3, 4 & 7 and 0.72 to 1 for examples 5 & 6. The resulting blends were agglomerated using a laboratory scale Sirman CV6 mixer, supplied by Metcalfe Catering Equipment Ltd, Blaenau Ffestiniog, Wales. The resulting wet agglomerates were then dried in an oven at 150°C for 12 hours, gently forced through a 420 micron screen and sieved at 150 microns to adjust the particle size distribution.

The resultant agglomerates have the following properties:

		<u>Ultrasonics</u>	<u>d10</u>	<u>d50</u>	<u>d90</u>
15	Example 3	0	186	306	488
		50	14	222	425
		100	3.8	23	62
20	Example 4	0	223	385	530
		50	9.4	151	423
		100	4	16	41
25	Example 5	0	32	233	460
		50	11	128	376
		100	3.9	17	45
	Example 6	0	199	386	554
30		50	8	180	412
		100	3	13	41
	Example 7	0	190	346	532
		50	30	286	510
35		100	4	16	46

Examples 8-10

The following homogeneous powder blends were made:

5	INGREDIENT	EX 8	EX 9	EX 10
	SORBOSIL AC77	26.3	43.1	60.0
	SORBOSIL TC15	26.3	43.1	40.0
10	POTASSIUM PYROPHOSPHATE	24.6		
	SODIUM PYROPHOSPHATE	19.8		
	ZINC CITRATE TRIHYDRATE		10.8	
15	TITANIUM DIOXIDE	3.0	3.0	

The powder blends were fed through a roller compactor Fitzpatrick Chilsonator model L83 (made by Fitzpatrick Company, Elmhurst, Illinois, USA) which was configured as Fig. 1 in the article "Preconditioning process powders with dry granulation" by Calvin E. Johnson (The Fitzpatrick Company), cited in Powder and Bulk Engineering December 1987. The upper screen size was 425 microns and the lower one was 250 microns.

The resultant agglomerated product had the following properties:

		<u>Ultrasonics</u>	<u>d10</u>	<u>d50</u>	<u>d90</u>
30	Example 8	0	150	326	526
		50	17	162	383
		100	4	29	69

19

Example 9	0	176	331	530
	50	74	292	516
	100	6.9	72	314

5	Example 10	0	160	300	497
		50	120	288	495
		100	3	15	69

Examples 11-14

10

The following homogeneous powder blends were made:

	INGREDIENT	EX11	EX12	EX13	EX14
	GASIL 23D		72.75	36.0	64.9
15	GASIL 23TP	50.0			
	SORBOSIL AC35		24.25	12.0	21.6
	GASIL 200TP	50.0			
	TITANIUM DIOXIDE		3.0	2.6	2.6
20	POTASSIUM CITRATE			43.3	
	ZINC CITRATE TRIHYDRATE			6.1	10.9

25 De-ionised water was added to the powder mixes (200g) to give a water:solids ratio of 1.33 to 1 for examples 11,12 & 14 and 0.72 to 1 for example 13. The resulting blends were agglomerated using a laboratory scale Sirman CV6 mixer, supplied by Metcalfe Catering Equipment Ltd, 30 Blaenau Ffestiniog, Wales.

The resulting wet agglomerates were then dried in an oven at 150°C for 12 hours, gently forced through a 420 micron screen and sieved at 150 microns to adjust the particle size distribution.

5

The resultant agglomerates have the following properties:

		<u>Ultrasonics</u>	<u>d10</u>	<u>d50</u>	<u>d90</u>
10	Example 11	0	197	354	526
		50	10	213	465
		100	3.3	15	50
15	Example 12	0	187	311	498
		50	16	250	471
		100	5	34	297
	Example 13	0	190	333	518
20		50	14	210	455
		100	4	24	69
	Example 14	0	196	326	514
		50	96	282	476
25		100	4	29	104

Examples 15-16

The following homogeneous powder blends were made:

INGREDIENT	EX 15	EX 16
BACO AF239	50.0	
CALCIUM PYROPHOSPHATE		50.0
SORBOSIL TC15	50.0	50.0

De-ionised water was added to the powder mixes (200g) to give a water:solids ratio of 1.33 to 1. The resulting blends were agglomerated using a laboratory scale Sirman CV6 mixer, supplied by Metcalfe Catering Equipment Ltd, Blaenau Ffestiniog, Wales.

The resulting wet agglomerates were then dried in an oven at 150°C for 12 hours, gently forced through a 420 micron screen and sieved at 150 microns to adjust the particle size distribution.

The resultant agglomerates have the following properties:

	Ultrasonics	d10	d50	d90
Example 15	0	219	379	536
	50	194	355	524
	100	6.7	43	186
Example 16	0	215	373	534
	50	177	339	517
	100	3	37	95

Examples 17-19

The following blends were made:

5	INGREDIENT	EX 17	EX 18	EX 19
	SORBOSIL AC77	44.2	43.9	44.45
	SORBOSIL TC15	44.1	43.9	44.45
	ZINC CITRATE TRIHYDRATE	11.0	10.7	11.76
10	COSMENYL BLUE A2R	0.7		0.07
	COSMENYL GREEN GG			0.27
	COSMETIC PINK RC 01		1.5	

15 De-ionised water was added to the powder mixes (200g) to
give a water:solids ratio of 1.33 to 1. With examples 17
& 19, the Cosmenyl pigment dispersions were added to the
de-ionised mixing water, which was then added to the
20 powder mix. The resulting blends were agglomerated using
a laboratory scale Sirman CV6 mixer, supplied by
Metcalf Catering Equipment Ltd, Blaenau Ffestiniog,
Wales.

25 The resulting wet agglomerates were then dried in an
oven at 150°C for 12 hours, gently forced through a 420
micron screen and sieved at 150 microns to adjust the
particle size distribution.

30 The resultant agglomerates have the following
properties:

23

		<u>Ultrasonics</u>	<u>d10</u>	<u>d50</u>	<u>d90</u>
	Example 17	0	182	301	487
		50	41	251	447
5		100	4	22	62
	Example 18	0	191	344	532
		50	163	347	534
10		100	5.6	39	210
	Example 19	0	192	345	537
		50	77	285	511
		100	4	19	49
15	<u>Example 20:</u>				

A toothpaste having the following composition was produced.

	INGREDIENT	% BY WEIGHT
	Sorbitol	45
	Water	22.12
	Sorbosil AC77	10.0
25	Silica of the Invention	7.0
	Sorbosil TC15	6.0
	PEG 1500	5.0
	SLS	1.5
	TiO ₂	1.0
30	Spearmint Flavour DP5017	0.5
	SMPF	0.8
	SCMC	0.8
	Saccharin	0.2
35	Sodium Benzoate	0.08

The above formulation was made under vacuum using conventional preparative procedures in a Lang mixer. In preparation 1 the flavour component was added over the side of the vessel near the end of the formulation.

5

A further identical preparation 2 was carried out except that the flavour was added to the silica granule of the invention by pipette prior to its introduction to the toothpaste mixer. The granule of the invention,
10 containing the flavour, was dry mixed with the other two silicas and the resultant powder mix was added in portions over 40 minutes under closed vacuum.

The two pastes were then examined "blind" by 6 people,
15 who were asked to assess the taste properties. All 6 people stated that paste 2 had a significantly stronger spearmint taste than paste 1, indicating that the granule of the invention could carry and deliver flavour more effectively than simply adding it to the toothpaste
20 mix separately.

CLAIMS

1. Granular composition comprising 45 to 98 % w/w of a
5 water insoluble particulate, whereby 10 to 75% of
the water insoluble particulate is made from a
water insoluble particulate material, having a
weight mean particle size of less than 20 microns
and an oil absorption capacity of 60 to 180g/100g,
10 and selected from the group consisting of amorphous
silicas, aluminas, calcium carbonates, dicalcium
phosphate, tribasic calcium phosphates, insoluble
sodium metaphosphate, calcium pyrophosphates,
hydroxyapatites, perlites, zeolites, magnesium
15 carbonate, pumice, and 10 to 75% of the water
insoluble particulate is made from a water
insoluble particulate material, having a weight
mean particle size of below 20 microns and an oil
absorption 200 to 350g/100g, selected from the
20 group consisting of amorphous silicas, low density
aluminas and expanded perlites, the granular
composition having a particle size, by sieve
analysis, of 95% below 600 microns and 95% above 40
microns.
25
2. Granular composition according to claim 1
comprising 1 to 5% w/w of TiO_2 .
3. Granular composition according to claims 1 & 2
30 comprising up to 15% zinc citrate.
4. Granular composition according to claim 1-3
characterised in that the agglomerate contains a
mater 1 having a cosmetic or therapeutic dental
35 benefit.

5. Granular composition according to claim 1-3 wherein the material having a cosmetic or therapeutic benefit is a flavour compound.
- 5 6. Granular composition according to claim 1-3 comprising a high structure silica thickener and a low structure silica abrasive.
- 10 7. Process for producing a granular composition according to claim 1 wherein, 10 to 75 parts by weight of a water insoluble particulate material, having a weight mean particle size of less than 20 microns and an oil absorption capacity of 60 to 180g/100g, and selected from the group consisting of 15 amorphous silicas, aluminas, calcium carbonates, dicalcium phosphate, tribasic calcium phosphates, insoluble sodium metaphosphate, calcium pyrophosphates, hydroxyapatites, perlites, zeolites, magnesium carbonate, pumice are mixed 20 with 10 to 75 parts by weight of a water insoluble particulate material, having a weight mean particle size of below 20 microns and an oil absorption 200 to 350g/100g, selected from the group consisting of amorphous silicas, low density aluminas and 25 expanded perlites, then agglomerated with water, the resulting product being then dried.
- 30 8. Process for producing a granular composition wherein, 10 to 75 parts by weight of a water insoluble particulate material, having a weight mean particle size of less than 20 microns and an oil absorption capacity of 60 to 180g/100g, and selected from the group consisting of amorphous 35 silicas, aluminas, calcium carbonates, dicalcium phosphate, tribasic calcium phosphates, insoluble

sodium metaphosphate, calcium pyrophosphates, hydroxyapatites, perlites, zeolites, magnesium carbonate, pumice are mixed with 10 to 75 parts by weight of a water insoluble particulate material, having a weight mean particle size of below 20 microns and an oil absorption 200 to 350g/100g, selected from the group consisting of amorphous silicas, low density aluminas and expanded perlites, the resulting blend being agglomerated by compaction.

9. Process according to claim 7 or 8 wherein TiO_2 and zinc citrate is added to the amorphous silica particles prior to agglomeration.

10. Process according to claim 7 wherein the agglomeration with water is done with a water:solids ratio of 1.1:1 to 1.35:1.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP 95/03560A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 A61K7/16

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 A61K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP,A,0 269 966 (KAO CORPORATION) 8 June 1988 cited in the application see the whole document ---	1,4-7
A	EP,A,0 473 171 (KAO CORPORATION) 4 March 1992 see the whole document ---	1,4-7
A	GB,A,2 272 640 (UNILEVER PLC.) 25 May 1994 see the whole document ---	1,4-7
A	US,A,4 089 943 (ROBERTS F. D. ET AL) 16 May 1978 ---	1,4-7
A	EP,A,0 268 763 (DEGUSSA AKTIENGESCHELLSCHAFT) 1 June 1988 see claims ---	1
-/--		

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

Z document member of the same patent family

Date of the actual completion of the international search

19 January 1996

Date of mailing of the international search report

08.02.96

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Couckuyt, P

INTERNATIONAL SEARCH REPORT

International Application No
PCI/EP 95/03560

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP,A,0 411 211 (UNILEVER PLC.) 6 February 1991 see the whole document ---	1,3
A	EP,A,0 272 380 (DEGUSSA AKTIENGESCHELLSCHAFT) 29 June 1988 see the whole document ---	1
A	WO,A,92 02454 (JOSEPH CROSFIELD & SONS LIMITED) 20 February 1992 see page 14; example -----	1

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PC1/EP 95/03560

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-0269966	08-06-88	DE-A- 3786754	02-09-93
		DE-T- 3786754	17-03-94
		ES-T- 2059347	16-11-94
		HK-A- 38094	29-04-94
		JP-A- 1038016	08-02-89
		SG-A- 35194	08-07-94
		US-A- 4871396	03-10-89
EP-A-0473171	04-03-92	DE-D- 69108142	20-04-95
		DE-T- 69108142	02-11-95
		ES-T- 2072501	16-07-95
		HK-A- 155295	06-10-95
		JP-A- 4124123	24-04-92
		US-A- 5149521	22-09-92
GB-A-2272640	25-05-94	NONE	
US-A-4089943	16-05-78	US-A- 3935306	27-01-76
EP-A-0268763	01-06-88	DE-A- 3639844	01-06-88
		DE-A- 3780917	10-09-92
		ES-T- 2051718	01-07-94
		US-A- 5124143	23-06-92
EP-A-0411211	06-02-91	DE-D- 68910125	25-11-93
		DE-T- 68910125	10-02-94
EP-A-0272380	29-06-88	DE-A- 3639845	01-06-88
		CA-A- 1324247	16-11-93
		CA-A- 1331503	23-08-94
		DE-A- 3780279	13-08-92
		JP-A- 6107409	19-04-94
		JP-A- 6107410	19-04-94
		JP-C- 1838888	25-04-94
		JP-A- 63139014	10-06-88
		US-A- 5110574	05-05-92
WO-A-9202454	20-02-92	EP-A- 0495039	22-07-92